

# worn tyre for wet-grip performances

Ongoing tests status – FRANCE



## Life test Study: New tyres VS Worn tyres (France)

- **Program remind** 
  - 2 tyres sizes (2 vehicles),
  - for each vehicles 2 tyres references (Premium & Quality)

### ₹ 3 steps

- Tests according to R117 as New states (trailer method)
- Wear on vehicle for up to 20 000 km per tyres (total of 4 Tyres references)
- ▼ Tests according to R117 as « Worn states ». For WG 2 tests proceed:
  - -Brand New ASTM16 & test with a worn ASTM16 according to candidates states. (trailer method)
- Study Schedule 2019-2020

Tyre Selection March 2019



REPORT March 2020

R117 tests as new May 2019

Tyre wear on Vehicle From June 2019

R117 test as Worn

R117 test as Worn From Oct to Nov 2019 From Jan to Feb 2020



## Life test Study: New tyres VS Worn tyres (France)

#### Tyres Selection

- Vehicle A: 195/55R20 95H Tall & Narrow (1 Premium tyre & 1 Quality tyre)
- Vehicle B: 235/50R18 101V SUV & Allroad (1 Premium tyre & 1 Quality tyre)

### Status January 2020

Study Schedule march 2019 to February 2020		Tread-depth measurements (New)	WG test "as new" (Trailer Method)	Wear life 20 000km (on vehicle)	WG test "worn 20 000km" (Trailer Method SRRT New)	WG test "worn 20 000km" (Trailer Method SRRT Worn)	Candidate Tread-depth measurements (Worn)
Vehicle A <b>Tall &amp; Narrow</b>	Candidate #1 195/55R20 - 95H	х	х	х	х	January 2020	December 2019
	Candidate #2 195/55R20 - 95H	х	х	From October to January	February 2020	February 2020	February 2020
Vehicle B	Candidate #3 235/50R18 - 101V	х	х	х	х	January 2020	December 2019
SUV & All Road	Candidate #4 235/50R18 - 101V	х	х	х	Х	January 2020	January 2020
SRTT16"	New Worn (Buffed)	X	X	N/A N/A	Х	×	

Done

In progress

Next step



## Life test Study: New tyres VS Worn tyres (France)

#### Measurments

Tests performed on RR & WG as New and Worn

#### First results

- As predicted RR improvement are confirmed
- WG are improved when using a « new SRTT »
- WG test using «worn SRTT» in progress

	New Tyres					
Ref.	Rolling Resistance	Wet Grip (New SRTT)				
PN9086	7,29	1,53				
PN9087	6,78	1,46				
PN9088	8,43	1,39				
PN9089	9,42	1,36				
	Worn Tyres					
Ref.	Rolling Resistance	Wet Grip (New	Δ (mm)			
Nei.	Rolling Resistance	SRTT)	new vs worn			
PN9086	7,00	1,56	0,87			
PN9087	6,63	1,61	1,49			
PN9088	7,73	1,36	0,00			
PN9089	#DIV/0!	#DIV/0!	2,26			





## THANK YOU FOR YOUR ATTENTION